

# SYSTEM BUILD UP GUIDE

## GP General Purpose Render



	Substrate Prep	Key Coat	Base Coat	Reinforcement	Finish
METHOD 1	-	-	[GP] 10-12mm	See page 21	[GP] 8-10mm
METHOD 2	-	[SB] 3-4mm*	[GP] 10-12mm	See page 21	[GP] 8-10mm

\* If hand applying – Key Coat can also be a spatterdash or stipple coat.



	Substrate Prep	Key Coat	Base Coat	Reinforcement	Finish
METHOD 1	QP X	-	[SB] 10mm	See page 21	[GP] 8-10mm
METHOD 2	-	[SB] 3-4mm*	[GP] 10-12mm	See page 21	[GP] 8-10mm

\* Key Coat can also be a spatterdash or stipple coat.



	Substrate Prep	Key Coat	Base Coat	Reinforcement	Finish
METHOD 1	QP X**	-	[SB] 10mm	See page 21	[GP] 8-10mm
METHOD 2	-	[SB] 3-4mm*	[GP] 10mm	See page 21	[GP] 8-10mm

\* If hand applying – Key Coat can also be a spatterdash or stipple coat. \*\* If brick is dusty and friable.



	Substrate Prep	Key Coat	Base Coat	Reinforcement	Finish
METHOD 1	QP X	-	[SB] 10mm	See page 21	[GP] 8-10mm
METHOD 2	QP X	[SB] 3-4mm*	[GP] 10mm	See page 21	[GP] 8-10mm

\* If hand applying – Key Coat can also be a spatterdash or stipple coat.



**NATURAL STONWORK**

Not suitable for this substrate if jointed/pointed with lime mortars.



**RENDER CARRIER BOARD**

Not suitable for this substrate.